

**HYDRAULIC OIL COMPOSITION FOR BUFFER**

**Patent number:** JP2000109877  
**Publication date:** 2000-04-18  
**Inventor:** KAMATA EIJI; OHASHI HIROSHI; OTSUKA NAOTO;  
NAKATANI YOSHITAKA; UENO KENJI  
**Applicant:** TONEN CORP; TOYOTA MOTOR CORP  
**Classification:**  
**- international:** **C10M169/04; C10M169/00;** (IPC1-7): C10M169/04;  
C10M101/02; C10M145/14; C10M169/04; C10N30/02;  
C10N30/06; C10N30/08; C10N40/08  
**- european:**  
**Application number:** JP19980288024 19981009  
**Priority number(s):** JP19980288024 19981009

Report a data error here

**Abstract of JP2000109877**

**PROBLEM TO BE SOLVED:** To obtain a hydraulic oil compsn. for buffers, which is excellent in low-temp. viscosity characteristics, vaporizability, and shear stability and has a stable damping power at from low to high temps. **SOLUTION:** This compsn. is prepd. by compounding, based on the compsn., at least 94 wt.% base oil comprising a mixed mineral oil consisting of (a) a deeply dewaxed mineral oil and (b) a low-viscosity mineral oil in a wt. ratio of (97/3)-(99/1) with 4-6 wt.% non-dispersion-type polymethacrylate viscosity index improver as an additive, and has a kinematic viscosity of 3-3.5 mm<sup>2</sup>/s at 100 deg.C and 20.5-23.5 mm<sup>2</sup>/s at 20 deg.C, a viscosity index of 160-170, a Brookfield viscosity of 1,350-1,600 mPa.s at -40 deg.C, an amt. of NOACK evaporation of 6 wt.% or lower, and a viscosity decrease of 7% or lower at 100 deg.C in the shear stability test by the sound wave method.

Data supplied from the esp@cenet database - Worldwide